

# CATENE TRASPORTO RESCHIANTI DI FUSIONE

CHAINS CONVEYOR RISK OF MELTING



□	CARICHI DI ROTTURA MEDI KN				*Stile
	MN 18MnCrB5	CN 18NiCrMo5	C45 C45	CD 42CrMo4	
codice maglia stampata	Cementazione temprata	Cementazione temprata	Bonifica	Bonifica	
	71	77	93	126	1
	110	120	150	210	1
	180	195	235	330	1
	163	175	212	290	1
	212	230	278	375	1
	180	195	235	330	1
	230	245	300	405	4
	290	320	370	550	1
	290	320	370	550	2
	290	320	370	550	3
	370	400	480	655	4
	440	470	570	790	1
	155	165	200	270	1
	190	205	250	330	1
	190	205	250	330	1
	227	245	300	405	1
	155	165	200	270	1
	320	342	420	560	7
	370	400	480	655	4
	900	950	1200	1600	3
	380	410	500	670	4
	500	540	660	900	4
	500	540	660	900	3
	585	630	765	1035	5
	585	630	765	1035	5
	710	760	930	1260	4
	735	790	960	1300	4
	735	860	1050	1430	4
	840	900	1100	1480	1
	840	900	1100	1480	1
	930	1000	1220	1650	4
	290	320	370	550	8
	440	470	570	790	8
	370	400	480	655	8
	540	580	705	955	8
	250	265	325	440	8
	380	410	500	670	8
	540	580	705	955	8
	380	410	500	670	8
	540	580	705	955	8
	975	1050	1270	1720	8



OGNIBENE S.P.A. \_ VIA DEL TIPOGRAFO, 6 \_ 40138 BOLOGNA \_ ITALY  
 TEL: +39 051 534225 \_ FAX: +39 051 535083  
[sales@ognibenechaintech.it](mailto:sales@ognibenechaintech.it) \_ [www.ognibenechaintech.com](http://www.ognibenechaintech.com)